

FERRO BORON

GfE Spec. 2000 005

Alloy

FeB 17-20% B

Production method

Aluminothermic reduction

Size

< 0.3 mm

Packaging

250 kg in steel drums

Composition

.....	spec. (wt. %)
B	17-22
Fe	balance
Al	max. 2
C	max. 0.1
P	max. 0.05
S	max. 0.05
Si	max. 1

other elements on request!