

FERRO BORON, STANDARD GRADE

GfE Spec.

2000 004

Alloy

FeB 17-20% B

Production method

Aluminothermic reduction

Size

lumpy up to 50 mm (2" x down)

Packaging

250 kg in steel drums

Composition

.....	spec. (wt. %)
B	17-21
Fe	balance
Al	max. 2
C	max. 0.1
P	max. 0.05
S	max. 0.05
Si	max. 1

other elements on request!