

FERRO NIOBIUM 40:60

GfE Spec.

2000 211

Alloy

FeNb 40:60

Production method

Aluminothermic reduction

Size

0.8 mm

Packaging

250 kg in steel drums

Composition

	spec. (wt. %)
Fe	balance
Nb	min. 60%
Al	max. 1.5
C	max. 0.1
Cr	max. 0.1
P	max. 0.05
S	max. 0.05
Si	max. 0.1
Ta	max. 0.05

other elements on request!