



_Ferro Vanadium 80
GfE Spec. 2000 018

Application

FeV 80 powder is used for the production of welding electrodes

Production method

Metallothermic reduction

Size

< 0.3 mm

Packaging

In sealed steel drums

Minimum Order Quantity

1,200 kg

(could vary +/- 10% due to production reasons)

Chemical Analysis in wt%

Fe	balance
V	75 - 84
Al	≤2
C	≤0.3
P	≤0.05
S	≤0.05
Si	≤1