



Nickel Niobium 40:60 Powder GfE Spec. 2000 197

Application

NiNb 40:60 powder is used for powdermetallurgical applications

Production method

Metallothermic reduction

Size

< 0.25 mm

Packaging

In sealed steel drums

Minimum Order Quantity

2,500 kg

(could vary +/- 10% due to production reasons)

Chemical Analysis in wt%

Nb	min. 58
Ni	balance
Al	≤1.5
C	≤0.1
Fe	≤1.0
P	≤0.03
S	≤0.02
Si	≤0.1
Ta	≤0.05