

**Nickel Niobium 40:60 High Purity**  
GfE Spec. 2000 196 / 2020 666

**Application**

NiNb 40:60 high purity is used as master alloy for the production of superalloys

**Production method**

Metallothermic reduction

**Size**

0 - 50 mm

**Packaging**

In sealed steel drums

**Chemical Analysis in wt%**

Nb	min. 58
Ni	balance
Al	≤1.0
C	≤0.05
Fe	≤1.0
P	≤0.03
Pb	≤0.005
S	≤0.01
Si	≤0.25
Ta	≤0.25
Ti	≤0.1
N	≤0.05
O	≤0.1