

A-Chromium Powder High Purity

GfE Spec. 2000 221

Application

For electrical switch contacts

Production method

Aluminothermic reduction

Size

63 – 150 μm
with < 63 μm max. 3 %
and > 150 μm max. 2 %

Packaging

In sealed steel drums



Chemical Analysis in wt%

Cr	≥ 99.3
Al	≤ 0.1
Al ₂ O ₃	≤ 0.1
C	≤ 0.01
Fe	≤ 0.5
K	≤ 0.002
Na	≤ 0.001
O	≤ 0.20
S	≤ 0.02
Si	≤ 0.1

No. 2 | June 2014