

A-Chromium Powder High Purity
GfE Spec. 2000 345

Application

For electrical switch contacts and coatings on cutting devices

Production method

Aluminothermic reduction

Size

< 300 µm

Packaging

In sealed steel drums



Chemical Analysis in wt%

Cr	≥99.3
Al	≤0.1
Fe	≤0.2
Si	≤0.1
C	≤0.01
O	≤0.10

No. 2 | June 2014