

A-Chromium Powder Pure

GfE Spec. 2000 350

Application

For electrical switch contacts, coatings on cutting devices, brake discs

Production method

Aluminothermic reduction

Size

0 - 80 μm
with max. 5% > 80 μm

Packaging

In sealed steel drums



Chemical Analysis in wt%

Cr	≥ 99.3
Fe	≤ 0.5
Si	≤ 0.1
C	≤ 0.02
O	≤ 0.3

No. 3 | January 2022