

_Niobium Chromium 80:20

GfE Spec. 2000 194

Application

NbCr 80:20 powder is used for production of welding electrodes

Production method

Metallothermic reduction

Size

< 0.3 mm

Packaging

In sealed steel drums

Minimum Order Quantity

1,500 kg

(could vary +/- 10% due to production reasons)

Chemical Analysis in wt%

Nb	77-83
Cr	bal.
Al	≤1.5
C	≤0.05
Fe	≤0.5
P	≤0.01
S	≤0.01
Si	≤0.5