

**A-Chromium Powder**  
GfE Spec. 2000 351

**Application**

For electrical switch contacts

**Production method**

Aluminothermic reduction

**Size**

0 – 45 µm  
with max. 5 % > 45 µm

**Packaging**

In sealed steel drums



**Chemical Analysis in wt%**

Cr	≥99.2
Fe	≤0.5
Si	≤0.2

No. 3 | January 2018