



\_Ferro Vanadium 60

GfE Spec. 2022 808 / 2022 809 / 2022 810  
2022 811 / 2022 812 / 2022 813

**Application**

FeV 60 powder is used for the production of welding electrodes

**Production method**

Metallothermic reduction

**Size**

0 – 0.2 mm	(GfE Spec. 2022 810)
0.063 – 0.2 mm	(GfE Spec. 2022 811)
0 – 0.25 mm	(GfE Spec. 2022 812)
0.075 – 0.25 mm	(GfE Spec. 2022 813)
0 – 0.3 mm	(GfE Spec. 2022 808)
0.063 – 0.3 mm	(GfE Spec. 2022 809)

**Packaging**

In sealed steel drums

**Minimum Order Quantity**

1,700 kg  
(could vary +/- 10% due to production reasons)

**Chemical Analysis in wt%**

Fe	balance
V	55 - 63
Al	≤2
C	≤0.3
P	≤0.05
S	≤0.05
Si	≤1