



Aluminum Molybdenum Vanadium 21:41:38  
GfE Spec. 2011 270

**Application**

AlMoV 21:41:38 is used as master alloy for the production of titanium alloys

**Production method**

Metallothermic reduction

**Quality**

Material

- a) visually inspected during manufacturing
- b) magnetically separated

**Size**

0 – 0.8 mm

**Packaging**

in sealed steel drums

**Chemical Analysis in wt%**

Al	19 - 23
Mo	39 - 43
V	36 - 40
B	≤0.005
C	≤0.10
Fe	≤0.40
Si	≤0.50
S	≤0.01
N	≤0.05
O	≤0.15