



## Nickel Zirconium 30:70 GfE Spec. 2022 650

### Application

NiZr 30:70 is used as master alloy for the production of super alloys and special alloys

### Production method

Vacuum induction melting and casting

### Size

Plates with approx. 300 x 150 x 70 mm

### Packaging

In sealed steel drums

### Chemical Analysis in wt%

|    |         |
|----|---------|
| Ni | balance |
| Zr | 68 - 72 |
| Ag | ≤0.002  |
| Al | ≤0.3    |
| Bi | ≤0.002  |
| C  | ≤0.1    |
| Fe | ≤1.0    |
| P  | ≤0.03   |
| Pb | ≤0.002  |
| S  | ≤0.03   |
| Se | ≤0.002  |
| Si | ≤0.2    |
| Te | ≤0.002  |

No. 1 | November 2016